- Gelcoat & Composites Polish-



## **Product Description**

Menzerna Premium Power Cut 200 is the ultimate cutting compound for gelcoat, CFRP, GFRP and other composites and plastics with maximum grinding effect and the latest technology. PPC 200 removes sanding marks, yellowing, clouding and signs of wear in the shortest possible time without damaging the surface. Premium Power Cut 200 does not contain any aggressive solvents and is therefore very user-friendly.

Cut:					10
Gloss:			6		

Color:	White	Surface
Density:	About 1,3 kg/l	- Gelco
Storage:	5-30 °C, avoid frost and direct sunlight	- Topco - GFRP - Perspo
Application:	Rotative	
Recommended speed:	1200-1800 rpm	- PE-rei
Maximum grinding removal:	P600-P800	- Boat p
Pad recommendation:	Double-sided lambswool pad	And ma
	Crater Shaped Lambswool Pad	

## e options:

- oat
- oat
- P, CFRP-Composites
- bex
- eisin
- paints
- any more!

Re	commended Usage

1	Clean surface thoroughly.
2	Shake the bottle and apply about 15 g of polishing compound to the double-sided lambswool pad.
3.	Work in a crossing motion. Apply strong, even pressure during polishing and run the product at a consistently low speed. When the product has been evenly distributed and worked into the surface after a few seconds, increase the speed. Work over as large an area as possible to reduce heat build-up at certain points.
4.	The polish is completely applied when only a slightly transparent or oily film is visible.
5.	Remove polish residues with a microfibre cloth. Optionally, clean with Menzerna Control Cleaner to check the polishing result.
6.	Sanding and wear marks are now removed. If required for a glossy surface, e.g. when working on dark paints, apply a Menzerna finish product to remove any holograms and polishing marks.

The Menzerna-System				
	1. Heavy Cut	2. Medium Cut	3. Finish	4. Protection
Standard products	PPC 200		SF 3500	
	MA 30		3F 3300	
Marine products	PPC 200			
	GC One-	Step-Polish	GC Premium Gloss	GC PP

Volumes	
Bottle, plastic, 1 litre	24017.281.001
Other containers upon request	t



YouTube

For more information on the products, see:

363 D



Menzerna.com

Important notice::

All the information above is based on our empirical values. Please test the use of our product yourself to determine whether it is suitable for your intended application. All matters related to the warranty and liability for this product are governed by our general selling terms and conditions, unless otherwise specified by applicable legal regulations.

How to find us: Menzerna Polishing Compounds GmbH &Co KG Industriestr. 25, D-76470 Ötigheim Tel.: +49-7222-9157-0 office@menzerna.com

15.10.18 - Copyright menzerna polishing compounds GmbH & CO KG - Entire, partially or in extracts use of this data is not permitted without agreement